



Sede Legale e Amministrativa:

Via A. Volta, 22
20094 Corsico MI
Tel. 02-45864671
Fax 02-45864423

www.soltecno.com

Uffici Commerciali e Magazzino:

Via delle Industrie – SP 20
26010 Bettolino di Salvirola CR
Tel. 0373-270405
Fax 0373-270397

Email: info@soltecno.com

TECHNICAL DATASHEET

TECNOCOL

UNIVERSAL SPRAY ADHESIVE

DESCRIPTION: Universal permanent adhesive, suitable for plastics, rubber, fabrics, metals, cork, leather, glass, wood, wallboards, paperboard, etc. It stands damp and temperatures up to 70°C.

COMPOSITION: Resins, petroleum based solvents, pressurized with LPG. It does not contain neoprene.

PHYSICAL AND CHEMICAL PROPERTIES:

Appearance	Aerosol container
Container size	400 ml
Color	colorless
Smell	usual solvent smell
Density	0.67 kg/l a 20°C
Pressure at 20°C	4 bar
Solubility	insoluble in water, soluble in most of organic solvents
Flash point	< 0°C (propellant)

HOW TO USE: Shake very well the can before use. Spray uniformly from a distance of about 20 cm on clean and dry surfaces. Wait for 2 or 3 minutes, then fit together the parts to be glued by maintaining a strong pressure on the contact surfaces for few seconds. Finally, in order to avoid valve clogging due to dry glue, turn the cap upside down and spray until the liquid stops leaking.

DANGER LABELLING:

Danger

H222 Extremely flammable aerosol.

H229 Pressurized container: may burst if heated.

H315 Causes skin irritation.

H319 Causes serious eye irritation.

H336 May cause drowsiness or dizziness.

H411 Toxic to aquatic life with long lasting effects.

GHS PICTOGRAMS:

GHS02 Flame

GHS07 Exclamation mark

GHS09 Dangerous for the environment

Note: the product contains Acetone, that has been included by Regulation EU 2019/1148 in the list of regulated explosive precursors. All suspicious transactions and significant disappearances and thefts must be reported to the relevant national contact point. This provision applies both to direct sales and to online sales.

Rev.: 3 – February 2022

Note: These notes are for information only and do not imply any responsibility on the part of Soltecno Srl. It is the responsibility of the customer to determine the suitability of the product prior to its processing. The data reported in this technical information describe the average indicative characteristics of the product: these are subject to change without notice and do not constitute sell specifications.